

Attorney Docket N . 5725.0656-00  
Application No.: 09/618,066

90. (Amended) A dermatological composition for at least one keratin material, a care composition for at least one keratin material, a make-up composition, a body hygiene composition, a sunscreen composition for at least one keratin material, or an after-sun composition for at least one keratin material comprising a composition comprising:

(a) at least one dyestuff; and

(b) at least one continuous liquid fatty phase comprising:

(i) at least one structuring polymer which has a weight-average molecular mass ranging from 1000 to 30,000 and comprises:

a) a polymeric skeleton comprising repeating units comprising at least one non-pendant hetero atom; and

b) at least one fatty chain, optionally functionalized, comprising from 12 to 120 carbon atoms, chosen from pendant fatty chains and terminal fatty chains which are bonded to said polymeric skeleton;

wherein said at least one fatty chain is present in a quantity ranging from 40% to 98% of the total number of all said repeating units comprising at least one non-pendant hetero atom and all said at least one fatty chains;

wherein said at least one dyestuff is chosen from pigments and nacres; and

wherein said composition is in the form of a structured, wax-free solid.

FINNEGAN  
HENDERSON  
FARABOW  
GARRETT &  
DUNNELL

1300 I Street, NW  
Washington, DC 20005  
202.408.4000  
Fax 202.408.4400  
www.finnegan.com

163. (Amended) A structured composition comprising:

(a) at least one dyestuff; and

(b) at least one continuous liquid fatty phase comprising:

Attorney Docket No. 5725.0656-00  
Application No.: 09/618,066

(i) at least one structuring polymer which has a weight-average molecular mass ranging from 1000 to 30,000 and comprises:

a) a polymeric skeleton comprising repeating units comprising at least one non-pendant hetero atom; and

b) at least one fatty chain, optionally functionalized, comprising from 12 to 120 carbon atoms, chosen from pendant fatty chains and terminal fatty chains which are bonded to said polymeric skeleton;

wherein said at least one fatty chain is present in a quantity ranging from 40% to 98% of the total number of all said repeating units comprising at least one non-pendant hetero atom and all said at least one fatty chains;

wherein said at least one continuous liquid fatty phase comprises greater than 40% by weight of the total weight of said at least one continuous liquid fatty phase of at least one apolar liquid oil;

wherein said structured composition is in the form of a wax-free solid;

wherein said at least one dyestuff is chosen from pigments and naces; and

wherein said at least one dyestuff, said at least one continuous liquid fatty phase and said at least one structuring polymer form a physiologically acceptable medium.

165. (Amended) A structured composition comprising:

(a) at least one dyestuff; and

(b) at least one continuous liquid fatty phase comprising:

(i) at least one structuring polymer which has a weight-average molecular mass ranging from 1000 to 30,000 and comprises:

FINNEGAN  
HENDERSON  
FARABOW  
GARRETT &  
DUNNER LLP

1300 I Street, NW  
Washington, DC 20005  
202.408.4000  
Fax 202.408.4400  
www.finnegan.com

Attorney Docket No. 5725.0656-00  
Application No.: 09/618,066

a) a polymeric skeleton comprising repeating units comprising at least one non-pendant hetero atom; and

b) at least one fatty chain, optionally functionalized, comprising from 12 to 120 carbon atoms, chosen from pendant fatty chains and terminal fatty chains which are bonded to said polymeric skeleton;

wherein said at least one fatty chain is present in a quantity ranging from 40% to 98% of the total number of all said repeating units comprising at least one non-pendant hetero atom and all said at least one fatty chains;

wherein said structuring polymer is chosen from polymers resulting from at least one polycondensation reaction between at least one dicarboxylic acid and at least one diamine;

wherein said structured composition is in the form of a wax-free solid;

wherein said at least one dyestuff is chosen from pigments and nacles; and

wherein said at least one dyestuff, said at least one continuous liquid fatty phase and said at least one structuring polymer form a physiologically acceptable medium.

--167. (New) A structured composition comprising:

(a) at least one dyestuff; and


(b) at least one continuous liquid fatty phase comprising at least one structuring polymer which has a weight-average molecular mass ranging from 1000 to 30,000;

wherein said at least one structuring polymer is chosen from polymers of formula (I) below and mixtures thereof:

FINNEGAN  
HENDERSON  
FARABOW  
GARRETT &  
DUNNER LLP

1300 I Street, NW  
Washington, DC 20005  
202.408.4000  
Fax 202.408.4400  
www.finnegan.com

Attorney Docket No. 5725.0656-00  
Application No.: 09/618,066



in which:

-  $n$  is an integer which represents the number of amide units such that the number of ester groups present in said at least one structuring polymer ranges from 10% to 50% of the total number of all said ester groups and all said amide groups comprised in said at least one structuring polymer;

-  $R^1$ , which are identical or different, are each chosen from alkyl groups comprising at least 4 carbon atoms and alkenyl groups comprising at least 4 carbon atoms;

-  $R^2$ , which are identical or different, are each chosen from  $C_4$  to  $C_{42}$  hydrocarbon-based groups with the proviso that at least 50% of  $R^2$  are chosen from  $C_{30}$  to  $C_{42}$  hydrocarbon-based groups;

-  $R^3$ , which are identical or different, are each chosen from organic groups comprising atoms chosen from carbon atoms, hydrogen atoms, oxygen atoms and nitrogen atoms with the proviso that  $R^3$  comprises at least 2 carbon atoms; and

-  $R^4$ , which are identical or different, are each chosen from hydrogen atoms,  $C_1$  to  $C_{10}$  alkyl groups and a direct bond to group chosen from  $R^3$  and another  $R^4$  such that when said at least one group is chosen from another  $R^4$ , the nitrogen atom to which both  $R^3$  and  $R^4$  are bonded forms part of a heterocyclic structure defined in part by  $R^4$ -N- $R^3$ , with the proviso that at least 50% of all  $R^4$  are chosen from hydrogen atoms;

FINNEGAN  
HENDERSON  
FARABOW  
GARRETT &  
DUNNER LLP

1300 I Street, NW  
Washington, DC 20005  
202-408.4000  
Fax 202.408.4400  
www.finnegan.com